

SVR CV60

Place of origin: Viet Nam

Description 製品説明

SVR CV60 is a constant viscosity grade. It is produced by only adding hydroxylamine neutral sulfate (HNS) to ammonia preserved field latex after reception at factory and before coagulation with acid.

The SVRCV60 rubber is processed through some stages such as crushing, creping, crumbing, drying and baling. The hydroxylamine inhibits the storage hardening reaction in natural rubber, which leads to an increase in its Mooney viscosity.

Features: Constant viscosity rubber without peptizer agent, Constant Mooney viscosity, uniformity, and softness.

Application: Vibration mountings for engines, Railway buffers, Injection moulded products.

SVR CV60 の特長は、SVR10CV そして SVR CV50 同様、安定的な粘度、柔らかさにあります。他の規格と異なる最大の特長は、解膠剤を一切使っていないという点にあります。微振動装置、鉄道の緩衝材、そして

Specifications 規格

Type of bales ペールタイプ	Crates 梱包用木枠	Shrink-wrapped 収縮包装
20.00 kg/bale	60 bales	60 bales
25.00 kg/bale	48 bales	48 bales
33.33 kg/bale	36 bales	36 bales
35.00 kg/bale	36 bales	36 bales

Dirt content	ダート含有量 (max %wt)	0.02	TCVN 6089: 2004 (ISO249: 1995)
Ash content	灰分含有量 (max %wt)	0.40	TCVN 6087: 2004 (ISO247: 1990)
Nitrogen content	窒素含有量 (max %wt)	0.60	TCVN 6091: 2004 (ISO1656: 1996)
Volatile matter	揮発分 (max %wt)	0.80	TCVN 6088: 2004 (ISO248: 1991)
Initial Plasticity	初期可塑性 (min)	-	TCVN 6092-2: 2004 (ISO2007: 1991)
Plasticity retention index	可塑保持指数 (min)	60	TCVN 6092-1: 2004 (ISO2930: 1995)
Lovibond Color Index	ロビボンダ指数 (max)	-	TCVN 6093: 2004 (ISO4660: 1990)
Mooney viscosity ML 100oC	トルクマックス	60(+5, -5)	TCVN 6090: 2004 (ISO268-1: 1994)
Cure 4	T90 (min)	8 - 11	TCVN 6094: 2004 (ISO3417: 1991)

* At time of production, ML 1+ 4 (100 oC)